

## Parquetkit

Revision: 17/09/2015

Page 1 from 2

### Technical data

|                                   |                     |
|-----------------------------------|---------------------|
| Basis                             | Acrylic dispersion  |
| Consistency                       | Paste               |
| Curing system                     | Physical drying     |
| Skin formation* (20°C / 65% R.H.) | Ca. 20 min          |
| Density                           | Ca. 1,50 g/ml       |
| Maximum allowed distortion        | 15 %                |
| Temperature resistance            | -20 °C → 80 °C      |
| Application temperature           | 5 °C → 30 °C        |
| Shrinkage                         | Ca. 15% (DIN 52451) |

(\*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

### Product description

Parquetkit is a high-quality, solvent free joint sealant, based on polyacrylics.

### Properties

- Solvent-, and silicon free
- Paintable
- Can be varnished with different kinds of parquet varnish.
- No odor

### Applications

- For the filling of joints with a maximum movement of 15%.
- Filling sealant for joints in parquet-, or laminate floors
- Connection joints between parquet floors, baseboards and walls
- Can also be used for joints in wooden floors.

### Packaging

Colour: light oak, middle oak, beech, maple, cherry, merbau

Packaging: 300 ml cartridge

### Shelf life

At least 18 months in unopened packaging in a dry storage place at temperatures between +5°C and +25°C. Protect against frost.

### Substrates

Substrates: All common timber and laminate floors as well as porous building surfaces. Not suitable for natural stone

Nature: clean, free of dust and grease.

Surface preparation: No pretreatment required  
We recommend a preliminary adhesion test on every surface.

### Joint dimensions

Min. width for joints: 5 mm

Max. width for joints: 20 mm

Min. depth for joints: 5 mm

Recommendation sealing jobs: joint width = joint depth.

### Application method

Application method: Apply the sealant by means of a manual or pneumatic caulking gun into the joint. Next finish with for example a filling-knife. Repeat in case of shrinking.

Sandable after minimum 24 hours.

Do not apply when rain or frost is imminent during curing process.

Cleaning: Before curing, Parquetkit can be removed with water from substrates and tools.

Finishing: Finishing with a soapy solution before skinning.

Repair: With the same material

### Health- and Safety Recommendations

Take the usual labour hygiene into account.

Consult the packaging label for more information.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

---

## Parquetkit

---

Revision: 17/09/2015

Page 2 from 2

### Remarks

- Do not use in applications where continuous water immersion is possible.
- Can be varnished with most varnishes.
- The lacquer or. varnish must be sufficiently elastic to allow application on a plasto-elastic sealant.
- Given the great diversity in available parquet lacquers and parquet varnishes it is recommended to do a compatibility test prior to application.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.